

EPDM AND SBR PELLETS

RAYSTON
products



Rubber pellets for synthetic flooring

DESCRIPTION

The EPDM and SBR rubber pellets are used combined with the Rayston Rubber Crumb Binders for sport surfaces, safety flooring, garden areas, roundabouts, recreational areas and other application in elastic flooring. The material can be applied by spraying or spreaders.

TECHINCAL DATA

INFORMATION ON THE PRODUCT BEFORE APPLICATION

	EPDM Pellets	SBR Pellets
Chemical description	EPDM rubber mixture, coloured	Rubber mixture SBR
Polymer content	21%	Liquid
Hardness Shore	60-65	60-70
Bulk density	600-700 g/l	100%
Particle size	1-4mm (90%)	1-4 mm (M8-version) 2-7 mm (M4-version)
Available colours	Red Green Bright green Dark blue Beige Yellow.	Black
Packaging	Plastic sacks, 25 kg each Pallets, 40 sacks each	Plastic sacks, 25 kg each Pallets, 48 sacks each
Storage	Keep at temperatures below 35°C, away from sunlight. Avoid contact with oils, solvents, petrol or related products.	
Use before	24 months after manufacturing date	

APPLICATION

Avoid contact with moisture before use. For specific instructions (dosage, mixing) for their use with the Rayston Rubber binders, refer to the relevant resin Technical Data Sheet. Usually, EPDM is reserved for exposed applications and SBR for underneath layers.

SAFETY

See information provided in the relevant Material Safety Data Sheet.

OTHER INFORMATION

The information contained in this DATA SHEET, as well as our advice, both written as verbal or provided through testing, are based on our experience, and they do not constitute any product guarantee for the installer, who must consider them as simple information.

We recommend to study deeply all information provided before proceeding to the use or application of any of our products, and strongly advise to conduct tests "on-site" in order to determine their convenience for a specific project.

Our recommendations do not exempt of the obligation of installers to deeply study the right application method for these systems before use, as well as to conduct as many preliminary tests as possible should any doubt arise. The application, use and processing of our products are beyond our control, and therefore under the exclusive responsibility of the installer. In consequence, the installer will be the only responsible of any damage derived from the partial or total in-observation of our indications, and in general, of the inappropriate use or application of these materials.

This Data Sheet supersedes previous versions.



KRYPTON CHEMICAL SL

C/ Martí i Franquès, 12 - Pol. Ind. les Tàpies
43890 - l'Hospitalet de l'Infant - Spain
Tel: +34 977 822 245 - Fax: +34 977 823 977

www.kryptonchemical.com - rayston@kryptonchemical.com

Latest update:

20/08/2022

Page:

1/1