



Decorative sand mixtures

DESCRIPTION

Quartz sand, natural or coloured with selected pigments with excellent quality and light resistance. Suitable for floors. Suitable for spreading over or as a filler for all kinds of floors made with Rayston products, both polyurethane and epoxy-based.

TECHNICAL DATA

INFORMATION ON THE PRODUCT

| | F 0-03 | F 01-03 | F 03-08 | FC 03-08 |
|-------------------|----------------------------------|----------------------------------|----------------------------------|---|
| Apparent density | 0.8 g/cm ³ | 1.7 g/cm ³ | 1.8 g/cm ³ | 0.6 g/m ² |
| Granulometry | 0-0.3 mm | 0.1-0.3 mm | 0.3-0.8 mm | 0.3-0.8 mm |
| Available colours | Natural quartz colour | Natural quartz colour | Natural quartz colour | 20 decorative combinations available. Special mixes on request. |
| Presentation | 25 kg bags 49 sack pallets | 25 kg bags 49 sack pallets | 25 kg bags 49 sack pallets | 25 kg bags 49 sack pallets |

APPLICATION GUIDELINES

Please refer to the resin Technical Data Sheet for specific guidance. Do not use wet material.

| | | |
|--|---|--|
| Fine leveling mortar Surface rigor <1 mm | Epoxy primer 100 + quartz sand (0.1-0.3mm) with a ratio of 1:0.5 | 1.7 kg/m ² /mm |
| Medium leveling mortar Surface rigor up to 2 mm | Epoxy primer 100 + quartz sand (0.1-0.3mm) with a ratio of 1:1 | 1.9 kg/m ² /mm |
| Self-leveling intermediate layer 1.5 to 3 mm | Epoxy primer 100 + quartz sand (0.1-0.3mm) with a ratio of 1:1 Optional quartz dusting (0.4-0.8mm) | 1.9 kg/m ² /mm Aprox 4 kg/m ² |

SAFETY

Always consult information provided in the Safety Data Sheet of this product.

OTHER INFORMATION

The information contained in this DATA SHEET, as well as our advice, both written as verbal or provided through testing, are based on our experience, and they do not constitute any product guarantee for the installer, who must consider them as simple information.

We recommend to study deeply all information provided before proceeding to the use or application of any of our products, and strongly advise to conduct tests "on-site" in order to determine their convenience for a specific project.

Our recommendations do not exempt of the obligation of installers to deeply study the right application method for these systems before use, as well as to conduct as many preliminary tests as possible should any doubt arise. The application, use and processing of our products are beyond our control, and therefore under the exclusive responsibility of the installer. In consequence, the installer will be the only responsible of any damage derived from the partial or total in-observation of our indications, and in general, of the inappropriate use or application of these materials.

This Data Sheet supersedes previous versions.